

### **Description**

Special PVC film white and transparent, in gloss, semi-gloss and matt surfaces

### **Release paper**

PE-coated silicone paper, 148g/m<sup>2</sup>, 168 µm

### **Adhesive**

Solvent polyacrylate, removable, grey and transparent

### **Area of use**

For brilliant and colourful digital advertising prints in short- and medium-term outdoor applications.

### **Printing method**

Inkjet printing with solvent based inks, UV- or Latex inks

### **Technical Data**

<b>Thickness*</b> (without protective paper and adhesive)	100 micron
<b>Dimensional stability</b> (FINAT TM 14)	adhered to steel, no shrinkage in cross direction, in length 0.4 mm max.
<b>Temperature resistance***</b>	adhered to aluminium, -40°C to +80°C, no variation
<b>Sea water resistance</b> (DIN 50021)	adhered to aluminium, after 100h/23°C no variation
<b>Resistance to solvents and chemicals</b>	at room temperature, 72h after adhesion to aluminium, short-term resistant to most oils and greases, fuels, aliphatic solvents, weak acids, salts and alkalis
<b>Fire behaviour</b>	adhered to steel, self-extinguishing
<b>Adhesive power*</b> (FINAT TM 1, after 24h, stainless steel)	8 N/25 mm
<b>Tensile strength</b> (DIN EN ISO 527)	along: min. 19 MPa across: min. 19 MPa
<b>Elongation at break</b> (DIN EN ISO 527)	along: min. 130% across: min. 150%
<b>Shelf life**</b>	2 years
<b>Application temperature</b>	> +8°C
<b>Service life by specialist application</b> under vertical outdoor exposure (normal climate of Central Europe)	5 years (not printed)
<b>Removability</b>	within 3 years residue-less removable from most surfaces

\* average

\*\* in original packaging, at 20°C and 50% relative humidity

\*\*\* normal climate of Central Europe

### **Note**

After printing the ink must be thoroughly dry in order to avoid any effect on the later combination with the laminate. Surfaces to which the material will be applied must be thoroughly cleaned from dust, grease or any contamination which could affect the adhesion of the material. Freshly lacquered or painted surfaces should be dried and cured completely. The compatibility of selected lacquers and paints should be tested by the user, prior to application of the material. Furthermore the application information published by ORAFOL is to be considered. The batch traceability according to ISO 9001 is possible on the basis of the roll number.

The statements in this information sheet are based upon our knowledge and practical experience. This data is intended only as a source of information and is given without guarantee and does not constitute a warranty. Due to the wide variety of possible uses and applications customers should independently determine the suitability of this material for their specific purpose, prior to use.